



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : G02B 6/22, 6/16</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/08142 (43) International Publication Date: 18 February 1999 (18.02.99)</p>
<p>(21) International Application Number: PCT/US98/15274 (22) International Filing Date: 23 July 1998 (23.07.98) (30) Priority Data: 60/054,821 7 August 1997 (07.08.97) US (71) Applicant (for all designated States except US): CORNING INCORPORATED [US/US]; 1 Riverfront Plaza, Corning, NY 14831 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): BERKEY, George, E. [US/US]; 11551 Riley Hill Road, Pine City, NY 14871 (US). (74) Agent: HERZFELD, Alexander, R.; Corning Incorporated, SP FR 02-12, Patent Dept., Corning, NY 14831 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report.</p>
<p>(54) Title: DISPERSION MANAGED OPTICAL WAVEGUIDE FIBER</p> <div data-bbox="477 1125 1110 1698"> </div> <p>(57) Abstract</p> <p>Disclosed is a single mode optical waveguide fiber designated for compensating for positive dispersion in optical telecommunications systems. A key characteristic of the invention is that the novel dispersion compensating waveguide, viz., a waveguide having large negative dispersion, contains no dopants, such as fluorine, which lower the refractive index of silica. A refractive index profile design which includes a high refractive index center segment (5) surrounded by a plurality of alternating high (6, 10, 13) and low refractive index segments, provides a dispersion compensation fiber which has the optical properties required for the system to be compensated without sacrificing bend resistance, increasing splicing loss, or elevating polarization mode dispersion.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

DISPERSION MANAGED OPTICAL WAVEGUIDE FIBER

Background of the Invention

5 The invention is directed to an optical waveguide fiber having a multi-ring core design which provides for large negative dispersion. In particular, the large negative dispersion is achieved while maintaining low bend loss, low splice loss, and polarization mode dispersion comparable to that of the waveguide fiber comprising the link to be compensated.

10 Many telecommunications links designed to operate in a wavelength window near 1300 nm have been installed. In general the waveguides manufactured for such links were designed to have a zero dispersion wavelength near 1300 nm to avoid signal distortion due to dispersion over long, unregenerated link lengths. More recently, the capability of operating at a wavelength window near 1550 nm has been developed. The 1550 nm
15 window is advantageous because the attenuation of a silica based waveguide has a minimum there and the window lies near the center of the erbium doped optical amplifier gain curve. In fact, for a typical waveguide the attenuation near 1550 nm is less than 60 % of the attenuation near 1300 nm. This large gain in signal to noise ratio as well as the possibility of extending link length
20 without adding regenerators has made telecommunications operations at 1550 nm very attractive.

However, if a telecommunication link originally made for 1300 nm window operation is to be upgraded to include 1550 nm operation, the dispersion penalty due to the location of the dispersion zero must be

overcome. Because the waveguides in these links were designed to have zero dispersion near 1300 nm, the dispersion at 1550 nm increases rapidly with link length. The dispersion at 1550 nm is typically about 15 -20 ps/nm-km.

Two strategies which may be used to remove the 1550 nm dispersion penalty are:

employ very narrow line width 1550 nm lasers; or,
introduce dispersion compensating waveguide fiber into the link.

A dispersion compensating waveguide fiber is one which has a dispersion of opposite sign relative to the link dispersion which is to be compensated. For example, a 1300 nm telecommunications system may have 18 ps/nm-km dispersion at 1550 nm. A link length of 60 km is common. Thus, for 1550 nm operation over this link 1080 ps per nm of laser line width must be compensated to avoid a dispersion penalty. Even though very narrow line width distributed feedback lasers have been developed a considerable amount of dispersion remains to be compensated at operating wavelengths far from the zero dispersion wavelength. Thus the dispersion compensating waveguide fiber can be used to advantage in systems employing very narrow linewidth lasers as well as lasers having a relatively broad emission band.

The technical innovations required to implement either of these strategies are sophisticated. In the case of the compensation waveguide strategy, waveguide core profiles which provide the proper amount of compensating dispersion must be found. The problem is complicated by the fact that changing the core refractive index profile to obtain a negative, i.e., compensating, dispersion, changes other properties of the waveguide. In particular, waveguide fibers having negative dispersion have been found to be more susceptible to bending loss, have higher polarization mode dispersion, and increased attenuation when compared to the original waveguide fiber used in the system. See, for example U.S. patent 5,361,319, Antos, et al.

The telecommunications industry, therefore, has a need for a dispersion compensating waveguide fiber which:

- is resistant to bending loss;

- has a high negative dispersion so that the compensating fiber length is relatively short;
- has a low attenuation;
- exhibits low splice loss with the original system waveguide; and,
- 5 - has comparatively low polarization mode dispersion.

Definitions

- 10 - The radius or width of the regions of the core are defined in terms of the index of refraction of the core along a radius. A particular region begins at the point where the refractive index characteristic of that region begins and ends at the last point where the refractive index is characteristic of that region. Radius and width will be expressed in terms of these beginning and ending points unless otherwise noted in the text.
- 15 - An alpha refractive index profile is $n = n_0(1 - \Delta(r/a)^\alpha)$, where n_0 is the refractive index at the first point of the alpha index profile, Δ is defined below, r is radius, and a is the radius measured from the first to the last point of the alpha index profile, and r is chosen to be zero at the first point of the alpha index profile.
- 20 - The width of an index profile segment is the distance between two vertical lines drawn from the respective beginning and ending points of the index profile segment to the horizontal axis of the chart of refractive index vs. radius.
- The % index delta is $\% \Delta = [(n_1^2 - n_c^2)/2n_1^2] \times 100$, where n_1 is a core index and n_c is the clad index. Unless otherwise stated, n_1 is the maximum refractive index in the core region characterized by a % Δ .
- 25 - The zero reference for refractive index is chosen as the minimum refractive index in the clad glass layer. A region of refractive index in the core which is less than this minimum value is assigned a negative value.
- Bend performance is defined by a standard testing procedure in which the attenuation induced by winding a waveguide fiber about a mandrel is
- 30 measured. The standard test calls for waveguide fiber performance with one turn about a 32 mm mandrel and with 100 turns about a 75 mm mandrel. The

maximum allowed bending induced attenuation is usually specified in the operating window around 1300 nm and around 1550 nm.

Summary of the Invention

5 The invention set forth in this application meets the need for a high performance dispersion compensating optical waveguide fiber without using fluorine.

10 A first aspect of the invention is a dispersion compensating single mode optical waveguide fiber having a central core region surrounded by a clad layer. To make the structure a waveguide, at least a portion of the core refractive index must be higher than the maximum refractive index of the clad layer which abuts and surrounds the core region. The core region of the novel dispersion compensating waveguide comprises at least five segments, a center segment symmetric about the long axis of the waveguide, and at least
15 four annular segments symmetrically layered about the center segment. The center segment has a relative index, Δ_c %, which is in the range of 1.5 % to 3.5 %. The upper limit on Δ_c % depends upon what is practical in terms of doping capability and in terms of added attenuation as dopant percent increases. Large negative dispersion can be obtained using a center relative index higher
20 than 3.5 %, but dopant levels high enough to produce such an index are usually impractical and not cost effective. A preferred range for Δ_c % is 2 % to 3 %.

25 The magnitudes of the relative indexes are all positive and are chosen as follows: the center relative index is largest; the successive odd numbered surrounding segments or layers, beginning with the number 1 for the layer abutting the center segment, are smaller in magnitude than Δ_c %; the successive even numbered surrounding layers are smaller in magnitude than Δ_c % but larger in magnitude than the odd numbered layers.

30 The center segment is characterized by a radius and the successive annular segments are characterized by widths. The novelty of the waveguide structure is defined by the choice of relative indexes, Δ %, and the center

radius and widths of the annular segments which make up the core. In particular, the Δ %'s and radius and widths are chosen such that the total dispersion of the waveguide is more negative than about -85 ps/nm-km. The waveguide attenuation depends upon the relative index of the center segment, Δ_c %. For Δ_c % near 2 % the attenuation is less than about 0.55 dB/km over a pre-selected band of wavelengths which lies in the wavelength range 1520 nm to 1600 nm. A wavelength of choice is near 1550 nm, which is an optimum operating wavelength for telecommunications. Average attenuation of 0.46 to 0.48 dB/km is typical for waveguide profiles having Δ_c % near 2 %. As Δ_c % approaches 3 % to 3.5 %, the upper limit of attenuation is about 1.5 dB/km. However, the higher Δ_c % profiles yield a larger negative dispersion, which means a shorter length of compensating waveguide is required. The novel dispersion compensating waveguide may be tailored for uses in which a longer length, lower attenuation waveguide is preferred as well as for uses in which a shorter length of waveguide is preferred, thereby requiring the waveguide to have a larger negative dispersion.

Further, the novel waveguide is characterized by an average splice loss of 0.5 dB and a bend loss no greater than 0.025 dB. The splice loss refers to splicing between the compensating waveguide and a waveguide in the system being compensated, which is usually a step index waveguide which is a standard in the industry. The bend resistance refers to the mandrel tests described in the definitions section.

In addition, the polarization mode dispersion is substantially the same as that for the waveguides of the system being compensated. Thus, the polarization mode dispersion may be expected to be no greater than about 0.5 ps/km^{1/2}.

In any of the embodiments described above, the shape of the respective core segments can be chosen from among the group of α -profiles, rounded step profiles, or trapezoidal profiles. The preferred shape is an α -profile with $\alpha = 0$ to 6 or a rounded step. Of these, the $\alpha = 1$ to 2 is a most preferred profile.

The Δ %'s of the even numbered annular segments or layers lie within the range of 0.2 to 0.6 of the center relative index, Δ_c %. As is noted above, the odd numbered segments are lower in magnitude than the even numbered segments. A particular embodiment of the invention has odd numbered segments for which the relative indexes are flat and close to zero.

A detailed embodiment of the 5 segment core (4 annular segments), in which the overall core radius is in the range 12 μm to 18 μm , is given in an example below.

Another embodiment described in detail below is a 7 segment core, i.e., one having 6 annular segments, in which the overall core radius is in the range 15.5 μm to 23.5 μm .

Brief Description of the Drawing

Fig. 1 is an illustration of the novel index profile showing the center segment and the annular core layers.

Fig. 2 is a measurement of a waveguide profile in which certain of the core segments have an index less than the clad index.

Fig. 3 is an index measurement of a 3 segment profile.

Fig. 4 is an index measurement of a 5 segment profile.

Fig. 5 is an index measurement of a 7 segment profile.

Description of the Preferred Embodiments

The novel refractive index profile described herein achieves the goal of large negative dispersion while retaining the advantageous properties of relatively low attenuation, low splice loss and bend loss, and polarization mode dispersion comparable to that of standard single mode optical waveguide fiber. In addition, the large negative dispersion is achieved without recourse to the use of dopants, such as fluorine, which reduce refractive index to less than that of silica. Use of fluorine can add several steps to the waveguide manufacturing process. Also, the placement is such that dopant type or concentration interfaces occur in the light carrying region of the waveguide.

Thus a process which eliminates fluorine greatly facilitates and cost reduces the manufacturing process.

5 The large negative dispersion provides for dispersion compensation using a relatively short length of compensating waveguide fiber, thus limiting the additional attenuation introduced into the system being compensated.

10 A general profile illustrative of the novel refractive index is shown in Fig. 1 which is a chart of relative index vs. waveguide radius. The main features of the refractive index profile are the high index center segment 2, the abutting annulus 4 of lower index, and a plurality of higher index rings exemplified by rings 6, 10, and 13. Alternative shapes for the respective center segment, low index segment and higher index segment are shown as dashed curves 5, 9, and 7. The definition of the width of an annular region is shown by horizontal axis segment 12. The end points defining the width may be conveniently chosen as the points at which the refractive index slope changes rapidly or changes from a constant as in the detailed embodiments given below. Note that the annular width is measured along the horizontal axis, i.e., the $\Delta = 0$ line. Another major feature of the refractive index profile is that $\Delta \%$ is nowhere negative, wherein silica is the reference refractive index. Thus the advantageous characteristics of the novel waveguide are achieved without resorting to index lowering dopants which typically are more difficult to incorporate and control. That is, undesirable multiple process steps and the introduction of an interface in the light carrying region of the waveguide are advantageously avoided.

25 A measured refractive index profile of a prior art dispersion compensating waveguide is shown in Fig. 2. Two regions of the core index profile, the center segment 14 and the ring segment 18 have positive $\Delta \%$. Both of the lower index segments, annular segments 16 and 20, have a minimum index which is negative, meaning that the two segments contain an index lowering dopant. A negative dispersion more negative than -70 ps/nm-km is possible using this profile design. However, in part due to the width and positioning of annular segment 18, the bend and splicing performance and the

30

polarization mode dispersion of the waveguide are not as good as standard single mode fiber. This performance deficiency together with the requirement of negative Δ %'s prompted the investigation of alternative profiles.

5 A measurement of a three segment profile is shown in Fig. 3. The center segment 22 is abutted by a low index annular segment 23 which in turn is abutted by a higher index annular ring 24. The design is simpler than that of Fig. 2 and the narrowing of annulus 24 as compared to annulus 18 of Fig. 2, provides for improved bend and splicing performance. However, the dispersion was found to be about -65 ps/nm-km which increases the length of the dispersion compensating fiber and so introduces a greater attenuation into the dispersion compensated system.

10 By comparison the novel refractive index profile shown measured in Fig. 4 provides for a dispersion more negative than about -85 ps/nm-km. The center segment, 26, has a Δ % is in the range of 1.5 to 3.5 %.

15 In an embodiment in which Δ_c % is 2 %, the radius 28 of the central segment is in the range 2 μ m to 3 μ m. The remainder of the core comprises four annular segments, 30, 32, 34, and 36, surrounding the center segment. The respective relative indexes follow the rule, Δ_c % $>$ Δ_2 % \geq Δ_4 % $>$ Δ_1 % \geq Δ_3 % \geq 0. The widths of the, for this case in which Δ_c % is 2%, respective annular segments, w_1 , w_2 , w_3 , and w_4 are in the ranges 2.4 μ m to 3.6 μ m, 1.6 μ m to 2.4 μ m, 0.8 μ m to 1.2 μ m, and 1.6 μ m to 2.4 μ m. In this case the widths are taken as the points at the beginning and end of a segment at which the slope of the index profile changes from a constant value. This definition of width is illustrated in Fig. 4 as lines 38 and 40. The total core radius 42, which is the sum of the central radius, the segment widths, and the index down taper to the clad layer index is 12 μ m to 18 μ m.

25 As Δ_c % tends toward its upper limit of about 3.5 %, the radius of the central region is reduced. For example at Δ_c % = 3 %, the radius of the central segment is in the range 1.2 μ m to 1.8 μ m. The widths of the remaining segments are not changed appreciably. The Δ %'s of the annuli 32 and 36 lie in the range of 0.2 to 0.6 of center relative index Δ_c %. The Δ % of the low

30

refractive index annular segments 30 and 34 are typically less than 20 % of the higher index annular ring segments and may be advantageously chosen to be at or near 0.

5 The novel refractive index profile illustrated in Fig. 4 has a high negative dispersion as well as good bend resistance and low splice loss. In addition, the other optical properties of the novel waveguide are such that it is suitable for use as a dispersion compensating waveguide. The high negative dispersion allows for compensation of positive dispersion in a telecommunications link using a relatively short length of the compensating waveguide. The relatively low attenuation, which can be less than 0.5 dB/km, depending upon choice of Δ_c %, of the compensating length of waveguide allows for acceptable signal to noise ratio in the system without need for an additional signal regenerator.

15 The seven segment embodiment of the novel refractive index is illustrated in Fig. 5. In the case in which Δ_c % is about 2 %, the central segment 46 has radius 44 in the range 2 μm to 3 μm and the respective widths w_1 , w_2 , w_3 , w_4 , w_5 , and w_6 , which are shown as 48, 50, 52, 54, 56, and 58 in Fig. 5., are in the ranges 2.9 μm to 4.4 μm , 1.25 μm to 1.90 μm , 0.75 μm to 1.10 μm , 0.9 μm to 1.35 μm , 0.9 μm to 1.35 μm , and 1.65 μm to 1.10 μm . These widths are defined as stated above in the 5 segment embodiment. The total core radius 60, which is the sum of the central radius, the segment widths, and the index down taper to the clad layer index is 15.70 μm to 23.50 μm .

25 The relative indexes of the core having seven segments, 46, 62, 64, 66, 68, 70 and 72, follow the rule, $\Delta_c \% > \Delta_2 \% \geq \Delta_4 \% \geq \Delta_6 > \Delta_1 \geq \Delta_3 \% \geq \Delta_5 \% \geq 0$. As Δ_c % moves toward its upper limit of 3.5 %, the central segment radius 44 decreases. For example, at Δ_c % = 3 %, the radius of the central segment is in the range 1.2 μm to 1.8 μm . The widths of the remaining segments are not changed appreciably, as stated for the embodiment of Fig. 4 described immediately above. The three high index annular segments 64, 68, and 72 are in the range of 0.2 to 0.6 of the center relative index Δ_c %. The Δ % of the low refractive index annular segments 62, 66, and 68 are typically less than 20

% of the higher index annular ring segments and may be advantageously chosen to be at or near 0.

5 The formation of a very high Δ % center together with a set of high Δ % annular segments spaced apart from the center segment and from each other by low index segments provides the surprising characteristic of large negative dispersion combined with excellent confinement of the signal light as shown by the good bend resistance.

Additional unusual and advantageous results are:

- 10
- attenuation is low;
 - cut off wavelength is compatible with the original system;
 - splice loss is low; and,
 - polarization mode dispersion is not degraded relative to the original system.

15 Although particular embodiments of the invention have been disclosed and described herein, the invention is nonetheless limited only by the following claims.

I claim:

1. A dispersion compensating single mode optical waveguide fiber comprising:

5 a central core glass region, surrounded by and in contact with a clad glass layer, at least a portion of the core glass region having a refractive index higher than the maximum refractive index of the clad layer, the central core glass region having a center, a refractive index profile, and a radius, and the clad glass layer having a refractive index profile,

10 in which, the refractive index profile of the central core region includes at least five segments,

a center segment having a cross sectional area distributed substantially symmetrically about the core center and having a relative index Δ_c %, which is in the range of 1.5 % to 3.5 %, and a radius,

15 a number j of annular segments surrounding the center segment beginning with a first annular segment abutting the center segment, a second annular segment abutting the first annular segment and a j th annular segment abutting the $(j-1)$ th segment to form a core having a center segment and j annular segments, the respective annular segments having a relative index Δ_j % and a width, w_j , measured along the Δ % = 0 line, where j is an integer ≥ 4 ;

20 in which Δ_c % > Δ_j % ≥ 0 for all values of j , and Δ_j for j an even number is greater than Δ_j for j an odd number;

25 in which the respective relative indexes, the center segment radius and annular segment widths are selected to provide a dispersion more negative than about -85 ps/nm-km at a pre-selected wavelength.

30 2. The dispersion compensating single mode waveguide of claim 1 in which the attenuation is no greater than about 1.5 dB/km, and for Δ_c % near 2 % is no greater than 0.55 dB/km, over a pre-selected band of wavelengths contained within the range 1520 nm to 1600 nm, and a splice loss which has an average of 0.5 dB for splices between the dispersion compensating

waveguide and standard step index single mode telecommunication waveguide fiber.

5 3. The dispersion compensating single mode waveguide of claim 1 in which $j = 4$ and the respective relative indexes are such that $\Delta_c \% > \Delta_2 \% \geq \Delta_4 \% > \Delta_1 \% \geq \Delta_3 \% \geq 0$ and the core radius is in the range $12 \mu\text{m}$ to $18 \mu\text{m}$.

10 4. The dispersion compensating single mode waveguide of claim 1 in which $j = 6$ and the respective relative indexes are such that $\Delta_c \% > \Delta_2 \% \geq \Delta_4 \% \geq \Delta_6 > \Delta_1 \geq \Delta_3 \% \geq \Delta_5 \% \geq 0$ and the core radius is in the range $15.5 \mu\text{m}$ to $23.5 \mu\text{m}$.

15 5. The dispersion compensating single mode waveguide of claim 3 or 4 in which the segments comprising the core each have a shape, the shape of the center segment selected from the group consisting of an α profile, a rounded step index profile, and a trapezoidal profile.

20 6. The dispersion compensating single mode waveguide of claim 5 in which α is in the range of about 0 to 6.

25 7. The dispersion compensating single mode waveguide of claim 3 in which the profile shape of annular segments 1 and 3 is a horizontal line and $\Delta_1 \% = \Delta_3 \%$ and $\Delta_1 \%$ is substantially zero and $\Delta_2 \%$ and $\Delta_4 \%$ may individually take on values in the range of 0.2 to 0.6 times the value of $\Delta_c \%$.

30 8. The dispersion compensating single mode waveguide of claim 4 in which the profile shape of annular segments 1, 3, and 5 is a horizontal line and $\Delta_1 \% = \Delta_3 \% = \Delta_5 \%$ and $\Delta_1 \%$ is substantially zero and $\Delta_2 \%$, $\Delta_4 \%$ and $\Delta_6 \%$ may individually take on values in the range of 0.2 to 0.6 times the value of $\Delta_c \%$.

9. The dispersion compensating single mode waveguide of claim 3 in which the profile shape of annular segments 2 and 4 is selected from the group consisting of an α profile, a rounded step index profile, and a trapezoidal profile.

5

10. The dispersion compensating single mode waveguide of claim 4 in which the profile shape of annular segments 2, 4, and 6 is selected from the group consisting of an α profile, a rounded step index profile, and a trapezoidal profile.

10


11. The dispersion compensating single mode waveguide of claim 7 in which the respective widths of the annular regions w_1 , w_2 , w_3 , and w_4 are in the ranges $2.4\text{ }\mu\text{m}$ to $3.6\text{ }\mu\text{m}$, $1.6\text{ }\mu\text{m}$ to $2.4\text{ }\mu\text{m}$, $0.8\text{ }\mu\text{m}$ to $1.2\text{ }\mu\text{m}$, and $1.6\text{ }\mu\text{m}$ to $2.4\text{ }\mu\text{m}$.

15


12. The dispersion compensating single mode waveguide of claim 8 in which the respective widths w_1 , w_2 , w_3 , w_4 , w_5 , and w_6 are in the ranges $2.9\text{ }\mu\text{m}$ to $4.4\text{ }\mu\text{m}$, $1.25\text{ }\mu\text{m}$ to $1.90\text{ }\mu\text{m}$, $0.75\text{ }\mu\text{m}$ to $1.10\text{ }\mu\text{m}$, $0.9\text{ }\mu\text{m}$ to $1.35\text{ }\mu\text{m}$, $0.9\text{ }\mu\text{m}$ to $1.35\text{ }\mu\text{m}$, and $1.65\text{ }\mu\text{m}$ to $1.10\text{ }\mu\text{m}$

1 / 5

FIG. 1



2 / 5



3 / 5




FIG. 3




FIG. 4




FIG. 5

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/15274

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 G02B6/22 G02B6/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G02B H04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 568 583 A (UMEDA ATSUSHI ET AL) 22 October 1996 see column 4, line 62 - line 67 see column 5 - column 8 see figures 1,4,5 ----	1
A	US 4 715 679 A (BHAGAVATULA VENKATA A) 29 December 1987 see figures 1-3,7-10 see column 3, line 42 - line 68 see column 4, line 1 - line 30 see column 7, line 67 - line 68 see column 8 - column 14 ----	1,5,9,10
A	US 4 149 772 A (IYENGAR RAMA ET AL) 17 April 1979 see the whole document -----	1,5,9,10

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

6 November 1998

Date of mailing of the international search report

16/11/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mathyssek, K

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 98/15274

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5568583	A	22-10-1996	CA 2157828 A	14-03-1996
			JP 8136758 A	31-05-1996
US 4715679	A	29-12-1987	AU 555648 B	02-10-1986
			AU 9104282 A	16-06-1983
			BR 8206652 A	01-11-1983
			CA 1205307 A	03-06-1986
			DK 502282 A,B,	08-06-1983
			EP 0083843 A	20-07-1983
			FI 824178 A,B	08-06-1983
			IN 156700 A	19-10-1985
			JP 1643785 C	28-02-1992
			JP 3005721 B	28-01-1991
			JP 58104040 A	21-06-1983
			AU 561632 B	14-05-1987
			AU 2808684 A	22-11-1984
			BR 8402305 A	26-12-1984
			CA 1246363 A	13-12-1988
			DK 246784 A,B	21-11-1984
			EP 0127408 A	05-12-1984
			FI 841998 A,B	21-11-1984
			HK 88790 A	09-11-1990
			IN 160397 A	11-07-1987
			JP 59226301 A	19-12-1984
US 4149772	A	17-04-1979	NONE	